



BLUE LABEL CO.,LTD.

48/58 Moo.1 Ekachai Road, Khok-Krabue, Amphur Muang, Samutsakhon, 74000 Thailand
Tel : +66 3449 4774-5 Fax : +66 3449 4776 Website : www.bluelabelgroup.com

Technical Data Sheet

RHINOZ – Innovation Special Products

RHINOZ[®] RF-102

RHINOZ Acrylic Skim 102

FEATURES

- Easy to apply by trowel
- High bonding strength
- Perfectly smooth finish
- High flexible
- Good weather resistance
- No crack and low smell
- Multi-layer coated without cracking
- Safe and environmentally friendly

DESCRIPTIONS

It is a skim smoothing rendering paste and ready to use formula for repairing surface defects in concrete or render. A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks and rock pockets. It is suitable for fiber cement, fiber concrete, gypsum concrete, especially for wall and ceiling with good adhesion and weathering resistance, perfectly smooth finish, high flexible, no crack, no chalk and can be sanded and paintable

APPLICATION

1. Surface must be clean, free of dust, oil, grease and other contaminates
2. Spray small amount of water on surface or use damp cloth wipe off surface before apply RHINOZ Acrylic Skim 102
3. Apply by stainless or steel trowel, apply one or several coats, can be recoated after 1-2 hours
4. It can be sanded after 16-24 hours and painting can be done after 24 hours
5. Clean tools and equipment with detergent and water

PACKING SIZE

5 kg. 25 kg.

STORAGE

Store in a dry place with shelf life 1 year in the original unopened packing

TECHNICAL DATA

Base	:	Acrylic polymer	
Appearance	:	Viscous paste	
Colour	:	See colour chart	
pH	:	8.0 - 10.0	
Density	:	1.5 - 1.6 g/cm ³	
Surface dry	:	15 - 20 minutes	(Depending on ambient conditions and thickness)
Recoating dry	:	1 - 2 hours	(Depending on ambient conditions and thickness)
Sand able	:	16 - 24 hours	(Depending on ambient conditions and thickness)
Cure time	:	7 days	(Depending on ambient conditions and thickness)
Bond strength	:	>1.5 N/mm ²	(ASTM D4541)
Coverage	:	1.2 kg./m ² /1 mm.	